



Product Data Sheet

Somos[®] Imagine 8000

Description

DSM's Somos[®] Imagine 8000 is a low-viscosity liquid photopolymer that produces water-resistant, durable and accurate three-dimensional parts. Somos[®] Imagine 8000 has a white, opaque appearance with performance that mirrors production plastics like ABS and PBT.

Applications

Somos[®] Imagine 8000 is ideal for many applications in the automotive, aerospace and consumer product industries. Somos[®] Imagine 8000 is successful in creating functional prototypes, humidity / water-resistant concept models, and durable low volume production parts.

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Opaque White
Viscosity	~340 cps @ 30°C
Density	~1.16 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	13.0 mJ/cm ²	[critical exposure]
D _p	6.25 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	64 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA			
Mechanical Properties		Somos® Imagine 8000	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Strength at Yield	47.2 - 47.6 MPa	6.8 - 6.9 ksi
D638M	Tensile Strength at Break	33.8 - 40.2 MPa	4.9 - 5.8 ksi
D638M	Elongation at Break	6 - 9%	6 - 9%
D638M	Elongation at Yield	3%	3%
D638M	Modulus of Elasticity	2,370 - 2,650 MPa	344 - 384 ksi
D638M	Poisson's Ratio	0.41	0.41
D790M	Flexural Strength	66.8 - 67.8 MPa	9.7 - 9.8 ksi
D790M	Flexural Modulus	2,178 - 2,222 MPa	315 - 322 ksi
D256A	Izod Impact (Notched)	23 - 29 J/cm	0.43 - 0.54 ft-lb/in
D3763	High Speed Puncture-Impact	4.6 J	3.36 ft-lb/in
D2240	Hardness (Shore D)	79	79
D570-98	Water Absorption	0.40%	0.40%

TECHNICAL DATA			
Thermal/Electrical Properties		Somos® Imagine 8000	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	63 µm/m°C	37 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	89 µm/m°C	52 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	170 µm/m°C	87 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	172 µm/m°C	100 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.8	3.8
D150-98	Dielectric Constant 1 KHz	3.7	3.7
D150-98	Dielectric Constant 1 MHz	3.4	3.4
D149-97A	Dielectric Strength	17.9 kV/mm	457 V/mil
E1545-00	Tg	41 - 43°C	111°F
D648	HDT @ 0.46 MPa (66 psi)	46°C	115°F
D648	HDT @ 1.81 MPa (264 psi)	41°C	105°F

DSM Functional Materials Somos® Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.
© 2012 DSM IP ASSETS B.V. All rights reserved.